

# The effect of Ca-Pb and P-As substitutions on the solubility of hydroxylapatites

Maria Młynarska, Bartosz Puzio, Monika Kwaśniak-Kominek, Maciej Manecki

AGH University of Science and Technology, Faculty of Geology, Geophysics and Environmental Protection, Department of Mineralogy, Petrography and Geochemistry; al. A. Mickiewicza 30, 30-059 Krakow, Poland; e-mail: mkmlynarska@gmail.com

© 2016 Authors. This is an open access publication, which can be used, distributed and reproduced in any medium according to the Creative Commons CC-BY 4.0 License requiring that the original work has been properly cited.

Hydroxylapatites are important biomaterials. Substitutions of Pb for Ca and As for P in hydroxylapatites are recently intensively studied due to their significance in the environmental immobilization of Pb and As (Lee et al. 2009, Chlebowska et al. 2015, Motyka et al. 2015). The general chemical formula of minerals in the apatite group is expressed by  $A_5(XO_4)_3Z$ , where A are bivalent cations (e.g.,  $Ca^{2+}$  or  $Pb^{2+}$ , cations are distributed on two distinct crystallographic sites),  $XO_4$  is a trivalent oxyanion (e.g.,  $PO_4^{3-}$ ,  $AsO_4^{3-}$ ), and Z is a monovalent anion (OH, F, Cl, or O). Positions Z and X may be partly filled with carbonate  $CO_3^{2-}$ . The structure of hydroxylapatite allows for unlimited substitutions of  $Pb^{2+}$  for  $Ca^{2+}$  and  $AsO_4^{3-}$  for  $PO_4^{3-}$ .

The ability of lead and arsenic apatites to immobilize these toxic elements result from their high durability and low solubility at the conditions on the Earth surface. Various apatites possess different thermodynamic properties including different solubility in aqueous solutions but the systematic variation of these properties in solid solution series is poorly understood.

The main objective of this research is determination of systematic variation in the solubilities of hydroxylapatites resulting from cationic substitutions of  $Pb^{2+}$  for  $Ca^{2+}$  and anionic substitutions of  $AsO_4^{3-}$  for  $PO_4^{3-}$  in their structure.

Three solid solution series were synthesized:

- HPY hydroxypyromorphite  $Pb_5(PO_4)_3OH$  – HAP hydroxyapatite  $Ca_5(PO_4)_3OH$ ,
- HMi hydroxymimetite  $Pb_5(AsO_4)_3OH$  – JBM johnbaumite  $Ca_5(AsO_4)_3OH$ ,

- HAP hydroxyapatite  $Ca_5(PO_4)_3OH$  – JBM johnbaumite  $Ca_5(AsO_4)_3OH$ .

The phases were synthesized from aqueous solutions at high pH above 8, at ambient temperature, by dropwise mixing of chemical reagents. The products are white, fine, homogeneous crystalline powders. Chemical composition determined by SEM/EDS is close to theoretical. X-ray diffraction confirms their crystalline structure and systematic changes in unit cell parameters with ionic substitution. Dissolution experiments were run in thermostatic bath at 25°C. An aliquot of 0.5 g of apatite was dissolved in 250 mL of 0.05M  $NH_4NO_3$  background solution at pH in the range of 3.5–5.0. Background solution was used to keep the ionic strength constant. The dissolution was carried out for 3 months. The bottles were manually stirred at least two times a week. The solution was syringe-sampled periodically and filtered through 0.2  $\mu m$  polycarbonate filter to remove the suspended solids. The concentration of Pb and Ca was determined by atomic absorption spectroscopy. The concentration of dissolved phosphates and arsenates was determined by UV-vis colorimetry using a molybdenum blue method. The plateau on concentration evolution patterns from the dissolution experiments was observed to determine equilibrium in the suspensions.

Dissolution of all the phases at the conditions of these experiments is incongruent. An increase in solution pH resulting from dissolution was observed in all cases. The system was considered in

equilibrium when at least three consecutive samples showed identical concentration of  $\text{Ca}^{2+}$  or  $\text{AsO}_4^{3-}$ . The equilibrium in HPY series was assumed by analogy. All the concentrations were recalculated to activities using PHREEQC model with Llnl database. The solubility  $K_{\text{sp}}$  determined for the endmembers at 25°C conform with the literature data and equal to:  $\text{HPY-}K_{\text{sp}} = 10^{-77.31}$ ,  $\text{HAP-}K_{\text{sp}} = 10^{-55.66}$ ,  $\text{HMi-}K_{\text{sp}} = 10^{-71.56}$ , and  $\text{JBM } K_{\text{sp}} = 10^{-37.76}$ . This confirms that, despite the incongruence of dissolution, the experimental procedure and the calculation scheme provide reliable approximation of the solubilities. The most soluble phase is johnbaumite  $\text{Ca}_5(\text{AsO}_4)_3\text{OH}$ . The solubility of all hydroxylapatites decreases linearly with the increase of Pb and P content. These trends do not correlate with the changes in Gibbs free energy of formation of the phases in question. This indicates that structural (e.g. the size of the ions) and the chemical factors (e.g. electronegativity)

play the dominant role in the solubility of substituted hydroxylapatites.

*This work was supported by AGH UST statutory grant No. 11.11.140.319.*

## REFERENCES

- Chlebowska P., Manecki M., Młynarska M. & Puzio B., 2015. Arsenate substitution in synthetic hydroxylapatite – structural characterization of the  $\text{Ca}_5(\text{PO}_4)_x(\text{AsO}_4)_{3-x}\text{OH}$  solid solution. *Geology, Geophysics and Environment*, 41, 1, 66–67.
- Lee Y.J., Stephens P.W., Tang Y., Li W., Phillips B.L., Parise J.B. & Reeder R.J., 2009. Arsenate substitution in hydroxylapatite: Structural characterization of the  $\text{Ca}_5(\text{P}_x\text{As}_{1-x}\text{O}_4)_3\text{OH}$  solid solution. *American Mineralogist*, 94, 666–675.
- Motyka A., Oknińska J. & Manecki M., 2015. Synthesis and mineralogical characteristics of hydroxylapatite-hydroxypyromorphite solid solution series  $\text{Ca}_5(\text{PO}_4)_3\text{OH} - \text{Pb}_5(\text{PO}_4)_3\text{OH}$ . *Geology, Geophysics and Environment*, 41, 1, 112–113.